



# ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.


## Quality Rubber Solutions



### TECHNICAL SPECIFICATIONS

QUALITY : NR / SBR RUBBER  
COIN MAT (CS 80)

Profile:



PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS	METHOD	METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.60	DIN 53508	1.60
HARDNESS	ASTM D2240	80 +/- 5 Sh A	DIN 53505	80 +/- 5 Sh A
TENSILE STRENGTH ( min )	ASTM D412	514 PSI	DIN 53504	35 kg/cm2
ELONGATION AT BREAK ( min )	ASTM D412	250%	DIN 53504	250%
ABRASION RESISTANCE ( max )	ASTM D5963	500 mm3	DIN 53516	400 mm3
COMPRESSION SET (70 °C/24 hrs/25% set) (max)	ASTM D395 METHOD B	40%	DIN 53517	40%
TEAR RESISTANCE ( Angular ) min	ASTM D624	112 Lbs/Inch	DIN 53515	16 Kg/cm
<b>CHANGE IN PROPERTIES</b>				
HEAT AGEING ( 72 hrs. AT 70°C )	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+20 / - 20		+20 / - 20
--- ELONGATION AT BREAK (%)		+25 / - 25		+25 / - 25
<b>VOLUME SWELL : AT 70° C FOR 72 HRS/IN</b>	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
<b>CHEMICAL RESISTANCE</b>				
--- OZONE	ASTM D 1149	NOT RECOMMENDED		NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
<b>TEMPERATURE RANGE</b>		-30° C to + 70° C		-30° C to + 70° C
<b>COLOUR</b>		BLACK		BLACK

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com) Website: [www.zenithrubber.com](http://www.zenithrubber.com)