



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : COMMERCIAL NEOPRENE RUBBER CODE: NE 80150

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.5	DIN 53508	1.50
HARDNESS	ASTM D2240	80 ± 5 Sh A	DIN 53505	80 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	427.5 PSI	DIN 53504	30 kg/cm2
ELONGATION AT BREAK (min)	ASTM D412	150%	DIN 53504	150%
COMPRESSION SET (70° C/24 hrs/25% set) (max)	ASTM D395 METHOD B	45%	DIN 53517	45%
TEAR RESISTANCE (Angular) min	ASTM D624	67 Lbs/Inch	DIN 53515	12 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70°C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10 / - 20		+10 / - 20
--- ELONGATION AT BREAK (%)		+10 / - 25		+10 / - 25
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO. 1		+ 23%		+ 23%
ASTM OIL NO. 2		+ 35%		+ 35%
ASTM OIL NO. 3		+ 85%		+ 85%
POLYMER CONTENT		10 %		10 %
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-35 °to + 80° C		-35 °to + 80° C
COLOUR		BLACK		

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com Website: www.zenithrubber.com