



ZENITH INDUSTRIAL RUBBER
PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : DIAPHRAGM RUBBER SHEETING WITH 1 PLY NYLON INSERTION CODE : DS 60140

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.4	DIN 53508	1.4
HARDNESS	ASTM D2240	60 ± 5 Sh A	DIN 53505	60 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	1362 PSI	DIN 53504	95 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	300%	DIN 53504	300%
ABRASION RESISTANCE (max)	ASTM D5963	300 mm ³	DIN 53516	300 mm ³
COMPRESSION SET (70° C/24 hrs/25% set) (max)	ASTM D395 METHOD B	0.4	DIN 53517	40%
TEAR RESISTANCE (Angular) min	ASTM D624	140 Lbs/Inch	DIN 53515	25 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70°C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10 / - 10		+10 / - 10
--- ELONGATION AT BREAK (%)		+10 / - 20		+10 / - 20
VOLUME SWELL : AT 40° C FOR 22 HRS/IN	ASTM D 471			
FUEL B		+ 25%		+ 25%
POLYMER CONTENT (NITRILE)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		EXCELLENT		EXCELLENT
--- SOLVENTS		GOOD		GOOD
TEMPERATURE RANGE		-35 °to + 110° C		-35 °to + 110° C
COLOUR		BLACK		

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com Website: www.zenithrubber.com