



# ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

**Quality Rubber Solutions**



## TECHNICAL SPECIFICATIONS

**QUALITY : VITON RUBBER SHEETING      CODE : FKM 80210**

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	2.10	DIN 53508	2.10
HARDNESS	ASTM D2240	80 ± 5 Sh A	DIN 53505	80 ± 5 Sh A
TENSILE STRENGTH ( min )	ASTM D412	570 PSI	DIN 53504	40 kg/cm2
ELONGATION AT BREAK ( min )	ASTM D412	150%	DIN 53504	150%
COMPRESSION SET (70 °C/24 hrs/25% set) (MAX)	ASTM D395 METHOD B	55%	DIN 53517	55%
TEAR RESISTANCE ( Angular ) min	ASTM D624	84 Lbs/Inch	DIN 53515	25 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING ( 72 hrs. AT 150 °C )	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		± 10		± 10
--- ELONGATION AT BREAK (%)		± 15		± 15
VOLUME SWELL : AT 150° C FOR 24 HRS/IN	ASTM D 471			
ASTM OIL NO.1		-0.06		-0.06
ASTM OIL NO.2		-0.01		-0.01
ASTM OIL NO.3		+ 5%		+ 5%
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	EXCELLENT		EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		VERY GOOD		VERY GOOD
--- SOLVENTS		VERY GOOD		VERY GOOD
TEMPERATURE RANGE		-30 ° to + 250° C		-30 ° to + 250° C
COLOUR		BLACK		BLACK

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com)

Website: [www.zenithrubber.com](http://www.zenithrubber.com)