



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : 100% NITRILE CODE : NB 65130

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.35	DIN 53508	1.35
HARDNESS	ASTM D2240	65 ± 5 Sh A	DIN 53505	65 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	1425 PSI	DIN 53504	100 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	350%	DIN 53504	350%
COMPRESSION SET (70 ° C/24 hrs/25% set) (max)	ASTM D395 METHOD B	0.25	DIN 53517	25%
TEAR RESISTANCE (Angular) min	ASTM D624	168 Lbs/Inch	DIN 53515	30 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70°C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -10		+ 10 / -10
--- ELONGATION AT BREAK (%)		+ 10 / -20		+ 10 / -20
VOLUME SWELL : AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		-0.03		-0.03
ASTM OIL NO.2		+ 1%		+ 1%
ASTM OIL NO.3		+ 9%		+ 9%
POLYMER CONTENT (HYPALON)		1		1
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		EXCELLENT		EXCELLENT
--- SOLVENTS		GOOD		GOOD
TEMPERATURE RANGE		-30 ° to + 110°C		-30 ° to + 110°C
COLOUR		BLACK		BLACK

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com

Website: www.zenithrubber.com

