



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : NITRILE RUBBER CODE : NB 65140

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.4	DIN 53508	1.4
HARDNESS	ASTM D2240	65 ± 5 Sh A	DIN 53505	65 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	1140 PSI	DIN 53504	80 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	400%	DIN 53504	400%
COMPRESSION SET (70 °C/24 hrs/25% set) (max)	ASTM D395 METHOD B	0.4	DIN 53517	40%
TEAR RESISTANCE (Angular) min	ASTM D624	112 Lbs/Inch	DIN 53515	20 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70 °C)	ASTM D573			
--- HARDNESS (Pts)		+ 4 (Max)		+ 4 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 15		+ 10 / - 15
--- ELONGATION AT BREAK (%)		+ 10 / - 20		+ 10 / - 20
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		+ 11%		+ 11%
ASTM OIL NO.2		+ 16%		+ 16%
ASTM OIL NO.3		+ 21%		+ 21%
POLYMER CONTENT (NITRILE)		100%		100%
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-35° to + 110° C		-35° to + 100° C
COLOUR		COLOUR		COLOUR

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com

Website: www.zenithrubber.com