



# ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

**Quality Rubber Solutions**



## TECHNICAL SPECIFICATIONS

**QUALITY : COMMERCIAL NATURAL RUBBER**

**CODE : ABE 50120**

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.20	DIN 53508	1.20
HARDNESS	ASTM D2240	50 ± 5 Sh A	DIN 53505	50 ± 5 Sh A
TENSILE STRENGTH ( min )	ASTM D412	1140 PSI	DIN 53504	80 kg/cm2
ELONGATION AT BREAK ( min )	ASTM D412	350%	DIN 53504	400%
ABRASION RESISTANCE ( max )	ASTM D5963	140 mm3	DIN 53516	140 mm3
COMPRESSION SET (70°C/24 hrs/25% set) (max)	ASTM D395 METHOD B	40%	DIN 53517	40%
TEAR RESISTANCE ( Angular ) min	ASTM D624	168 Lbs/Inch	DIN 53515	30 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING ( 72 hrs. AT 70°C )	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
--- ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / - 25
VOLUME SWELL : AT 70°C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	NOT RECOMMENDED		NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 80°C		-40° to + 70°C
COLOUR		BLACK		BLACK

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com)

Website: [www.zenithrubber.com](http://www.zenithrubber.com)