



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : COMMERCIAL NATURAL RUBBER CODE : NR 60130

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.35	DIN 53508	1.35
HARDNESS	ASTM D2240	60 ± 5 Sh A	DIN 53505	60 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	710 PSI	DIN 53504	50 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	3	DIN 53504	3
ABRASION RESISTANCE (max)	ASTM D5963	300 mm ³	DIN 53516	300 mm ³
COMPRESSION SET (70°C/24 hrs/25% set) (max)	ASTM D395 METHOD B	50%	DIN 53517	50%
TEAR RESISTANCE (Angular) min	ASTM D624	123 Lbs/Inch	DIN 53515	22 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70 °C)	ASTM D573			
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25		+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25		+ 10 / -25
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	NOT RECOMMENDED		NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70 °C		-30° to + 70 °C

COLOUR		BLACK		BLACK
A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020. Email: info@zenithrubber.com Website: www.zenithrubber.com				

