



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : NR 60140

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.4 ± 0.05	DIN 53508	1.4 ± 0.05
HARDNESS	ASTM D2240	60 ± 5 Sh A	DIN 53505	60 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	930 PSI	DIN 53504	65 kg/cm ²
ELONGATION AT BREAK (min)	ASTM D412	300%	DIN 53504	350%
COMPRESSION SET (70 0 C/22 hrs/25% set) (max)	TM D395 METHO	45%	DIN 53517	45%
ABRASION RESISTANCE, MM3, MAX	ASTM D 5963	350	DIN 53516	350
TEAR RESISTANCE (Angular) min	ASTM D624	112 Lbs/Inch	DIN 53515	20 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70 0C)	ASTM D 573			
--- HARDNESS (Pts)		+ 5 (MAX)		+ 5 (MAX)
--- TENSILE STRENGTH (%)		+20/ -20		+20/ -20
--- ELONGATION AT BREAK (%)		+25/ -25		+25/ -25
VOLUME SWELL : AT 700 C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
ASTM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	NOT RECOMMENDED		NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
RESISTANCE TO MIGRATION STAINING		GOOD		GOOD
TEMPERATURE RANGE		-300C + 70 0C		-300C + 800C
COLOUR		COLOR		

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com

Website: www.zenithrubber.com