



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions



TECHNICAL SPECIFICATIONS

QUALITY : SILICON RUBBER SHEETING CODE : SI 60130

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.3	DIN 53508	1.3
HARDNESS	ASTM D2240	60 ± 5 Sh A	DIN 53505	60 ± 5 Sh A
TENSILE STRENGTH (min)	ASTM D412	858 PSI	DIN 53504	60 kg/cm2
ELONGATION AT BREAK (min)	ASTM D412	200%	DIN 53504	200%
COMPRESSION SET (70 ° C/24 hrs/25% set) (max)	ASTM D395 METHOD B	45%	DIN 53517	50%
TEAR RESISTANCE (Angular) min	ASTM D624	95 Lbs/Inch	DIN 53515	17 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 100 °C)	ASTM D573			
--- HARDNESS (Pts)		+ 1 (Max)		+ 1 (Max)
--- TENSILE STRENGTH (%)		+ 5 / - 5		+ 5 / - 5
--- ELONGATION AT BREAK (%)		+ 5 / - 5		+ 5 / - 5
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		-0.01		-0.01
ASTM OIL NO.2		+ 7%		+ 7%
ASTM OIL NO.3		+ 17%		+ 17%
CHEMICAL RESISTANCE				
--- OZONE	ASTM D 1149	EXCELLENT		EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-90 °to + 200 °C		-90 °to + 200 °C
COLOUR		RED		RED

A/2, PAREKH MAHAL, 80 VEER NARIMAN ROAD, CHURCHGATE MUMBAI - 400 020.

Email: info@zenithrubber.com

Website: www.zenithrubber.com