


NR 70162
PRODUCT CODE – NR 70162



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.60 ± 0.05	ASTM D297	1.60 ± 0.05
HARDNESS	DIN 53505	70 ± 5 Sh A	ASTM D2240	70 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	426 PSI	ASTM D412	30 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	200 %	ASTM D412	200 %
TEAR RESISTANCE (Angular) min	DIN 53515	112 Lbs/Inch	ASTM D624	20 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (max)		+5 (max)
--- TENSILE STRENGTH (%)		+10 / -25		+10 / -25
--- ELONGATION AT BREAK (%)		+10 / -25		+10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		NOT RECOMMENDED		NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70° C		-30° to + 70° C
COLOR		BLACK		BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*

