


NB 65140

PRODUCT CODE – NB 65140 (50 %)



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.40 ± 0.05	ASTM D297	1.40 ±0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	710 PSI	ASTM D412	50 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	250%	ASTM D412	250 %
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	40 %	ASTM D395 METHOD B	40 %
TEAR RESISTANCE (Angular) min	DIN 53515	112 Lbs/Inch	ASTM D624	20 Kg/cm
CHANGE IN PROPERTIES AFTER HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10/-20		+10/-20
--- ELONGATION AT BREAK (%)		+10/-25		+10/-25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		+ 15%		+ 15%
IN IRM OIL NO.902		+ 25%		+ 25%
IN IRM OIL NO.903		+ 65%		+ 65%
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		FAIR		FAIR
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 90° C		-30 ° to + 90° C
COLOR		BLACK		BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*

