

SILICON 60120 PRODUCT CODE – SI 60120







TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.20 ± 0.05	ASTM D297	1.20 ± 0.05
HARDNESS	DIN 53505	60 ± 5 Sh A	ASTM D2240	$60 \pm 5 \text{ Sh A}$
TENSILE STRENGTH (min)	DIN 53504	1140 PSI	ASTM D412	80 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	300 %	ASTM D412	300 %
TEAR RESISTANCE (Angular) min	DIN 53515	140 Lbs/Inch	ASTM D624	25 Kg/cm
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	40 %	ASTM D395 METHOD B	40 %
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	ТМ
HARDNESS (Pts)		+3 (max)		+3 (max)
TENSILE STRENGTH (%)		+5 / 5		+5 / -5
ELONGATION AT BREAK (%)		+5 / -5		+5 / - 5
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		EXCELLENT		EXCELLENT
DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-90° to + 220° C		-90° to + 220° C
COLOR		GREY / BLACK		GREY / BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*







DSIR







