

#### GOVERNMENT OF INDIA RECOGNISED EXPORT HOUSE

# सत्यमेव जयते

### DCHT 60125 DIAMOND CHECKERED MAT PRODUCT CODE – CDHT 60125

## 0

#### **TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	-	1.25±0.05	ASTM D297	1.25 ±0.05
HARDNESS	ISO 48-4	$60 \pm 5$ Sh A	ASTM D2240	$60 \pm 5 \text{ Sh A}$
TENSILE STRENGTH ( min )	ISO 37	1777 PSI	ASTM D412	125 kg/cm 2
ELONGATION AT BREAK (min)	ISO 37	350%	ASTM D412	350 %
ABRASION RESISTANCE ( max )	ISO 4649	140 mm3 (10 N)	ASTM D5963	140 mm3 (10 N)
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	30 %	ASTM D395 METHOD B	30 %
TEAR RESISTANCE (Angular) min	ISO 34-1	168 Lbs/Inch	ASTM D624	30 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C )			ASTM D573	TM
HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max )
TENSILE STRENGTH (%)		+10/-25		+10 /- 25
ELONGATION AT BREAK (%)		+10/-25		+10 /- 25
VOLUME SWELL : AT 70°C FOR 72 HRS			AST <mark>M D</mark> 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		FAIR	ASTM D 1149	FAIR
DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70° C		-30 ° to + 70° C
COLOR		BLACK		BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*















