


Abra-Skirt 45

PRODUCT CODE – Abra-Skirt 45



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.18 ± 0.05	ASTM D297	1.18 ±0.05
HARDNESS	DIN 53505	45 ± 5 Sh A	ASTM D2240	45 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	1706 PSI	ASTM D412	120 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	400%	ASTM D412	400 %
ABRASION RESISTANCE (max)	DIN 53516	150 mm3 (5 N)	ASTM D5963	150 mm3 (5 N)
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	35 %	ASTM D395 METHOD B	35 %
TEAR RESISTANCE (Angular) min	DIN 53515	40 Lbs/Inch	ASTM D624	25 Kg/cm
CHANGE IN PROPERTIES AFTER HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10/-25		+10 /- 25
--- ELONGATION AT BREAK (%)		+10/-25		+10 /- 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-25° to + 70° C		-25 ° to + 70° C
COLOR		GREEN, BLACK, ORANGE		GREEN, BLACK ,ORANGE
FINISH	BOTH SIDE SMOOTH FINISH			

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*

