


Abra-Skirt 65

PRODUCT CODE – Abra-Skirt 65



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES	
		FPS UNITS	FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.35 ±0.05	ASTM D297 1.35 ±0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	ASTM D2240 65 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	853 PSI	ASTM D412 60 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	300%	ASTM D412 300 %
TEAR RESISTANCE (Angular) min	DIN 53515	112 Lbs/Inch	ASTM D624 20 Kg/cm
CHANGE IN PROPERTIES AFTER			
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573 TM
--- HARDNESS (Pts)		+ 5 (Max)	+ 5 (Max)
--- TENSILE STRENGTH (%)		+10/-25	+10/- 25
--- ELONGATION AT BREAK (%)		+10/-25	+10/- 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471
IN IRM OIL NO.901		NOT RECOMMENDED	NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED	NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED	NOT RECOMMENDED
CHEMICAL RESISTANCE			
--- OZONE		NOT RECOMMENDED	ASTM D 1149 NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED	NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED	NOT RECOMMENDED
--- OILS		NOT RECOMMENDED	NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED	NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70° C	-30 ° to + 70° C
COLOR		BLACK	BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*