


## **HYPALON 60130**PRODUCT CODE – HN 60130 (100%)



## **TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY		$1.30 \pm 0.05$	ASTM D297	$1.30 \pm 0.05$
HARDNESS	ISO 48-4	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH ( min )	ISO 37	1422 PSI	ASTM D412	100 kg/cm 2
ELONGATION AT BREAK ( min )	ISO 37	350%	ASTM D412	350 %
TEAR RESISTANCE (Angular) min	ISO 34-1	129 Lbs/Inch	ASTM D624	23 Kg/cm
ABRASION RESISTANCE (max)	ISO 4649	300 mm <sup>3</sup>	IS 3400 (Part 3)	300 mm <sup>3</sup>
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	TM
HARDNESS (Pts)		+ 3 (Max)		+ 3 (Max)
TEN <mark>SIL</mark> E STRENGTH (%)		± 10		± 10
ELONGATION AT BREAK (%)		± 10		± 10
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		+ 10%		+ 10%
IN IRM OIL NO.902		+18%		+18%
IN IRM OIL NO.903		+25%		+25%
CHEMICAL RESISTANCE				
OZONE		EXCELLENT	ASTM D 1149	EXCELLENT
DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
CONCENTRATED ACIDS AND BASES		GOOD		GOOD
OILS		MODERATE		MODERATE
SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-30° to + 140° C		-30° to + 140° C
COLOR		BLACK		BLACK
FINISH	BOTH SIDE SMOOTH FINISH			

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*























