


**NBR 70140**
**PRODUCT CODE – NB 70140 (30%)**

**TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY		1.45 ± 0.05	ASTM D297	1.45 ± 0.05
HARDNESS	ISO 48-4	70 ± 5 Sh A	ASTM D2240	70 ± 5 Sh A
TENSILE STRENGTH ( min )	ISO 37	711 PSI	ASTM D412	50 kg/cm 2
ELONGATION AT BREAK ( min )	ISO 37	250 %	ASTM D412	250 %
TEAR RESISTANCE ( Angular ) min	ISO 34-1	112 Lbs/Inch	ASTM D624	20 Kg/cm
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	40 %	ASTM D395 METHOD B	40 %
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR ( 72 hrs. AT 70 °C )			ASTM D573	
--- HARDNESS (Pts)		+5 (max)		+5 (max)
--- TENSILE STRENGTH (%)		+10 / -20		+10 / -20
--- ELONGATION AT BREAK (%)		+10 / -25		+10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		+ 15		+15
IN IRM OIL NO.902		+25		+25
IN IRM OIL NO.903		+65		+65
CHEMICAL RESISTANCE				
--- OZONE		FAIR		FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		FAIR		FAIR
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 90° C		-30° to + 90° C
COLOR		BLACK		BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*